



AuroraCell – Product Overview

Contact

Sodium-Ion Battery Cells

Info@aurora-cell.com

Product	Chem.	Ah	Vnom	V window	Wh	Max Charge (C cont./pulse)	Max Discharge (C cont./pulse)	Tmin chg/dis (°C)	Cycle life
CYLINDRICAL CELLS									
LO-32140-10E Battery Cell	Layered Oxide SIB	10.0	3.0	1.5-4.0	30.0	3C / 3C	10C / 20C	-20/-40	>2.000*
LO-32140-10P Battery Cell	Layered Oxide SIB	10.0	3.0	1.5-4.0	30.0	5C / 5C	18C / 30C	-20/-40	>2.000*
NFPP-32140-7Ah Battery Cell	NFPP SIB	7.0	3.0	1.5-3.4	21.0	1C / 1C	20C / 30C	-10/-40	>3.000*
3270 Battery Cell	NaCrO ₂ SIB	4.0	2.9	2.0-3.4	11.6	1C / 4C	16C / 30C	0/-40	>20.000*
33140AL Battery Cell	NaCrO ₂ SIB	8.3	2.9	2.0-3.4	24.1	1C / 4C	8C / 20C	0/-40	>20.000*
60145 Battery Cell	NFPP SIB	28.0	2.9	1.5-3.5	81.2	1C / 1C	3C / 3C	0/-40	>2.000*
NaFR14500HG-HP0.5 Cell	Layered Oxide SIB	0.5	3.0	1.5-4.0	1.5	4C / 10C	20C / 40C	0/-40	>1.000*
NaFR18650HG-HP1.2 Cell	Layered Oxide SIB	1.2	3.0	1.5-4.0	3.6	4C / 4C	20C / 40C	0/-40	>1.000*
PRISMATIC CELLS									
210Ah Prismatic Cell	NaCrO ₂ SIB	210.0	2.9	2.0-3.4	609	0.5C / 0.5C	1C / 1C	0/-40	>30.000*
175Ah Prismatic Cell	NFPP SIB	175.0	2.9	1.5-3.5	508	2C / 2C	2C / 2C	-10/-40	>8.000*
170Ah NFPP Prismatic Cell	NFPP SIB	170.0	2.85	1.5-3.4	484.5	1C / 1C	2C / 2C	-10/-40	>12.000*
70Ah Prismatic Power Cell	NaCrO ₂ SIB	70.0	2.9	2.0-3.4	203	2 / 4C	5C / 5C	0/-40	>30.000*
50Ah Prismatic Cell	NFPP SIB	50.0	2.85	1.5-3.4	142.5	2C / 2C	6C / 6C	-20/-40	>6.000*

Notes: Rates shown as continuous / pulse where applicable. Tmin shows minimum charge/discharge temperature in °C.

* 100% DoD at 25°C